

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-017033

(43)Date of publication of application : 18.01.2000

(51)Int.Cl. C08G 18/00  
B29C 41/18  
C08G 18/10  
C08G 18/66  
C08G 18/80  
C08K 5/00  
C08K 5/29  
C08L 75/04  
// (C08L 75/04  
C08L101:00 )  
B29K 75:00

(21)Application number : 10-189990

(71)Applicant : SANYO CHEM IND LTD  
TOYOTA MOTOR CORP

(22)Date of filing : 06.07.1998

(72)Inventor : OMORI HIDEKI  
TAKAI YOSHITSUGU  
UKAI JUNZO  
NISHIMURA HIDEO  
KOBAYASHI KAZUO

## (54) POLYURETHANE RESIN SLUSH MOLDING MATERIAL

### (57)Abstract:

PROBLEM TO BE SOLVED: To obtain a slush molding material broad in the moldable temperature range and excellent in moldability compared to the conventional ones using a silica based anti-blocking agent and capable of giving molded products excellent in low-temperature characteristics, fog resistance, heat aging characteristics, light aging characteristics or the like.

SOLUTION: The objective polyurethane resin slush molding material comprises (A) a thermoplastic polyurethane elastomer having a number average molecular weight of 10,000-50,000, a glass transition temperature of not higher than -35° C, and a heat softening initiation temperature of 100-160° C, (B) a plasticizer, (C) a blocked polyisocyanate, (D) a pigment, and (E) an anti-blocking agent. In this instance, the component (E) is a resin powder which does not thermally soften at a temperature of not higher than 160° C and has an average particle diameter of not greater than 10  $\mu$  m.

## LEGAL STATUS

[Date of request for examination] 02.08.1999

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3327840

[Date of registration] 12.07.2002

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]